REPORT DOCUMENTATION PAGE

Form Approved
OMB No. 0704-0188

1. REPORT DATE *(DD-MM-YYYY)*	2. REPORT TYPE	3. DATES COVERED *(From - To)*
30 April 2003	View Graphs	

4. TITLE AND SUBTITLE

T^2 Success within the Material Applications Branch of AFRL's Propulsion Directorate

5a. CONTRACT NUMBER

5b. GRANT NUMBER

5c. PROGRAM ELEMENT NUMBER

6. AUTHOR(S)

Shawn Phillips

5d. PROJECT NUMBER
2303

5e. TASK NUMBER
M1A3

5f. WORK UNIT NUMBER

7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES)

Air Force Research Laboratory (AFMC)
AFRL/PRSM
10 E. Saturn Blvd.
Edwards AFB, CA 93524-7680

8. PERFORMING ORGANIZATION REPORT NUMBER

AFRL-PR-ED-VG-2003-114

9. SPONSORING / MONITORING AGENCY NAME(S) AND ADDRESS(ES)

Air Force Research Laboratory (AFMC)
AFRL/PRS
5 Pollux Drive
Edwards AFB CA 93524-7048

10. SPONSOR/MONITOR'S ACRONYM(S)

11. SPONSOR/MONITOR'S NUMBER(S)
AFRL-PR-ED-VG-2003-114

12. DISTRIBUTION / AVAILABILITY STATEMENT

Approved for public release; distribution unlimited.

13. SUPPLEMENTARY NOTES

14. ABSTRACT

15. SUBJECT TERMS

16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT	18. NUMBER OF PAGES	19a. NAME OF RESPONSIBLE PERSON
					Sheila Benner
a. REPORT	b. ABSTRACT	c. THIS PAGE	A		19b. TELEPHONE NUMBER *(include area code)*
Unclassified	Unclassified	Unclassified			(661) 275-5693

FILE

MEMORANDUM FOR PRS (In-House Publication)

FROM: PROI (STINFO)

01 May 2003

SUBJECT: Authorization for Release of Technical Information, Control Number: **AFRL-PR-ED-VG-2003-114**
Shawn Phillips (AFRL/PRSM), "T^2 Success within the Material Applications Branch of AFRL's Propulsion Directorate"

6270

National Symposium Federal Lab Consortium
(Phoenix, AZ, no date provided) (Deadline: 06 May 2003 – RUSH per Dr. Corley) **(Statement A)**

T^2 Success within the Material Applications Branch of AFRL's Propulsion Directorate

- *Nanostructured™ Chemical Technology Based on POSS*
- *Rapid Processing for the Densification of Carbon-Carbon*

Dr. Shawn Phillips
Chief, AFRL/PRSM
Propulsion Directorate
Air Force Research Laboratory
Shawn.phillips@edwards.af.mil



Hybrid Plastics™

- Quick Note on Technology Transition

- Technology Transfer Success Stories w/in AFRL/PRSM
  - The Stories on:
    - a new chemical feedstock with no current market (yes with some science)
    - a new processing technology that already has an existing market.
  - That was then and this is now

- What will be contained in the Success Stories
  - Setting up collaborations
    - Spin-off companies (CRADAs)
    - Industrial Interest (NDAs, STTRs, SBIRs)
    - Industrial Funding (CRADAs)

  - Leveraging of resources (TIAs, CRADAs, NDAs, STTRs, SBIRs, PRDAs, DARPA, AFOSR, Academic Collaboration/Consultants)

The Council for Chemical Research Collaboration Success Award for 2001/2

POSS

2000 FLC Technology Transfer Award

Hybrid Plastics™

Commercialization and Solution Development

Basic and Applied Research

UCI University of California, Irvine

Discovery Research

Anatomy of a Polyhedral Oligomeric Silsesquioxane (POSS™) Molecule

Nonreactive organic (R) groups for solubilization and compatibilization.



May possess one or more functional groups suitable for polymerization or grafting.

Nanoscopic in size with an Si-Si distance of 0.5 nm and a R-R distance of 1.5 nm.

Thermally and chemically robust hybrid (organic-inorganic) framework.

Precise three-dimensional structure for molecular level reinforcement of polymer segments and coils.

POSS®: Versatile Feedstock Development

Completely Condensed





R = Me, Et, *i*-Bu, Cp, Cy, i-Octyl, Ph







Incompletely Condensed



R = Cp, Cy, *i*-Bu



R = Cy, Cp, i-Bu, Et



R = *i*-Butyl, Et

Functionalized POSS™-Monomers



Hybrid Plastics currently offers over 180 Nanostructured™ Chemicals

Key Aspects of POSS™ Technology

Hybrid (inorganic/organic) Composition



Nanostructured™ Chemical Reinforcement





POSS™ technology does not require manufacturers to retool or alter existing processes.

Lichtenhan et. al. *Macromolecules* **1993**, *26*, 2141.
Lichtenhan, *Polym. Mater. Encyclopedia* **1996**, *10*, 7768.

Where Are We Now?



2nd CRADA:

Focused on POSS Polymer Synthesis & Scale-up
(1st CRADA for new feedstocks/monomers)

Research:

New Monomers & Feedstocks (>180) - simplicity
Control & Prediction of Property Enhancements

Production:

Multi-Ton Production Capability!!!
10-100x Reduction in Cost (monomer dependent)!!!

Application:

Critical & High-Risk Paths for Air Force Applications
Incorporation and R&D Testing by Numerous Companies

POSS™-Technology Timeline



UCI Chemistry

Air Force Chemistry & Polymers

Hybrid Plastics Commercial Solutions



- NSF Funding
- 3 Academic Groups





Reverse Scale-up?





- 1992 AFOSR Funding of AFRL/PRSM
- 1992 AFRL Funding of AFRL/PRSM
- 1994-1998 Numerous NDAs, small funding to Universities
- 1994-??? Over 8 SBIRs focused on POSS Applications
- 1997 AFOSR funds academics for POSS research
- 1998 CRADA
- 1998 Multi-Million dollar ATP Grant for price reduction

Leveraging DOC program

NIST ATP Funded Cost Reduction



Hybrid Plastics™

Combined Material & Labor Costs Relative to Volume



Regression analysis for POSS™ manufacturing process.



- >25 Academic group in U.S.
- >100 Companies testing POSS



Nanostructured™ POSS Chemicals
Physical Form of Products



Crystalline Solids
Wide melting range 24°C to 400°C+

Waxes

Liquids & Oils
Wide viscosity range 40cSt. to 400cSt

Hybrid Plastics™

POSS™ Applications: Now Leveraged Primarily by Tech Transfer Company

R&D Through Market Development

R&D Chemicals and Nanotechnology Markets

Aldrich Chemical Co.
Gelest Inc.
Hybrid Plastics



Monomers & Polymers

Aerospace
Electronics
Medical
Composites
Packaging

Blendable Agents

Viscosity Modifiers
Processing Aids
Fire Retardants
Performance Additives
Corrosion Resistance

Catalysis

Metathesis
Epoxidation
Ligands
Supports

Biology & Agriculture

Drug Delivery
Medical Prosthetics
Pharmaceuticals
Antifungal Agents

Space-Survivable Polymers



Satellites & Space Systems

LEO Environment (Altitudes of 200 to 1500 km)

- Atomic Oxygen (AO): ~10^8 atoms/cm^3
- Actual AO flux on spacecraft ~10^{15} atoms/cm^2•s
- AO Collision energy ~ **5eV**
- Low-energy and high energy charged particles.
- Thermal cycling -50 to 150°C
- Solar VUV and UV radiation (~ 150 – 400 nm).

Bond	Dissociation Energy (EV)	λ (nm)	Material
$-C_6H_4-C(=O)-$	3.9	320	Kapton®
C-N	3.2	390	Kapton®
Si-O	8.3	150	Nanocomposite

Objectives

- Increase Space Survivability (AO, particle & VUV radiation, thermal cycling) of Polymeric Materials
- Self-Passivating/Self-Rigidizing/Self-Healing based on Hybrid organic/ inorganic nanocomposite incorporation

Tri-collaborative Effort for Proposed High-Risk, High-Payoff Program (Industry, Academia & Government)

Hybrid Plastics™

POSS-Aniline Synthesis.
Scale up and Validation.

DARPA

AIR FORCE RESEARCH LABORATORY

UNIVERSITY OF FLORIDA

MONTANA STATE UNIVERSITY BOZEMAN

Space Survivability Testing:
Includes erosion yields, surface Topographical, and in-situ analysis of POSS polymers following atomic oxygen and vacuum ultraviolet radiation exposure .

Michigan State University
Thermal, mechanical, and dielectric Properties of POSS-polyimides.

POSS-Polymeric Materials Group
Materials Application Branch
AFRL, Edwards AFB

Efficient cost effective POSS-Aniline Monomer and POSS-Polyimide Synthesis.
Development, characterization, and testing of POSS-Polyimide composite materials with high temperature stability and space survivability.

tsi

TRITON SYSTEMS INC

POSS Incorporation in Triton's High Performance Polyimide Resins:
Triton RTM PMR polyimides and NASA and Triton's co-developed Phosphine Oxide Polyimides.
Scale up and Validation.

THE AEROSPACE CORPORATION

Space Survivability Testing:
Includes simulated GEO exposure and mechanical property testing prior to and following exposure.

Stephanie Wunder-POSS Based PEO Electrolytes for Li Ion Batteries

Conductivity of $Q_8M_8^{PEO(n)}$ and $LiClO_2$





DSC Data: Crystallinity completely suppressed on attachment of PEO(n=4)



POSS PEO n=4

$H-(OCH_2-CH_2)_4-OH$

No observable Tg

Tm= -27°C

σ of PEO at RT is ~ 10^{-5}

σ goal for PEO-based solid polymer electrolytes is 10^{-3}

POSS Conference 2002

Dave Scheraldi: POSS PET

Tires are typically Reinforced with PET Fabrics

PET Tg
polymer 78° C
HMLS yarn ~ 110° C

Internal Tire Temperature
~ 120° C



TrisilanolisooctylPOSS PET Blend



Scheraldi (Case Western) and KOSA investigating processing parameters for POSS blended with PET tire cord

POSS Conference 2002

Masanori Ikeda: Flame resistant POSS PPE

Asahi-KASEI Corporation: Hybrid Plastics Asian Distributor



Figure 8. Effects of Additives on MFR and Anti-Flammability



Figure 10. Cross Section Photograph of Burned Test Piece

Isobutyl POSS cage in PPE gives:
superior flame retardance
imparts superb processability
excellent HDT is maintained

POSS Conference 2002

A Super Lab Created from the Ground Up



Collaboration Tools Employed

- Cooperative Research and Development Agreements
- Research and Agreements
- Small Business Development Centers
- Memorandum Agreements
- Confidentiality Agreements
- Contractual and Subcontractual Agreements
- Termsheets
- Option Agreements
- Assignment, Patent, and Licensing Agreements

Keys to Success for the POSS™-Team

(1) Committed Team - shared interests

(2) Talented People - persistent and skilled

(3) Clear Common Goals - cost & simplicity

(4) Communication - weekly

(5) Flexibility - find and reinforce success

(6) Resources - finances and facility

(7) We all had something to gain!!!

What did the Air Force Gain?

- **Sustainment of technology for DoD**
- Increased leverage of 6.1/6.2 IR&D funding
- Additional external customer funding
- Increased technical competency

Events Facilitating the Collaboration

1991-1998: Collaboration history between UCI and the Air Force
1996: Assignment of initial POSS patents to UDRI
1996: Execution of a conduit (third party client) CRADA to UDRI
1997: Significant increase of commercial interest in POSS
1998: Creation of a commercial spin-off (Hybrid Plastics)
1998: Award of $2M NIST ATP grant to Hybrid Plastics
1998: Execution of a conduit CRADA between AFRL and HP
1999: WTN completes commercialization report
2000: POSS™ receives FLC Technology Transfer Award
2000: POSS™ receives R&D Top 100 Award
2001/2: POSS-Team receives Council of Chemical Research Award

Rapid Densification of Carbon-Carbon: A Similar Story

2001 FLC Technology Transfer Award!

- Carbon-Carbon Advantages
  - Excellent High Temperature Structural Material
  - Very Reliable in Rocket Nozzles, Exit Cones, Nosetips, and Leading Edges As Well As Aircraft Brakes
- Drawbacks to Carbon-Carbon
  - SOTA Production of Carbon-Carbon Is Very Expensive
  - Carbon-Carbon Oxidizes at High Temperature in the Presence of Oxidizers



Objectives

- Decrease the processing time of Carbon-Carbon composites from many months to less than two weeks.
- Cut the densification cost in half.



F-22



Protective Sleeve for Spin-arrest Parachute

Rapid Densification of Carbon-Carbon

Technical Challenge:

- **With Conventional Liquid Phase Processes There Is Incomplete Penetration of the Liquids Due To:**
  - **a.) High Viscosity**
  - **b.) High Surface Tension**
  - **c.) Gassing of Precursor**



- **With Gas Phase Processes There Is Incomplete Penetration of the Gases Due to Their Decomposition on the Outer Surface**

In-Situ Formation of Carbon and Ceramic Matrices



Process Advantages & Recent Success

- Very Uniform Density
- Can Densify Thick Composite
- Complex Geometries
- No Need to Graphitize
- No Need to Machine Outside of Billet



•This is a CAT Scan of the middle of a 10" cubic block of carbon-carbon for the PBCS that has been densified with two In Situ cycles. Density variation is ± 2%

In Situ Densification Accomplishments (F-16 Brake)



70% of World C-C brake market is being worked with!

Does all this hard work pay off?

- 2 Generation Leap for U.S. Propulsion
- Numerous programs to aid the Warfighter
- Dramatic reduction in cost due to commercialization
- Royalties for the researchers!!!!